

## Preface

---

# ***Spray-Applied Rigid Polyurethane Foam Insulation, Medium Density***

## Scope

This Evaluation Listing applies to spray-applied rigid polyurethane foam, medium density, intended for use as thermal insulation for both building and non-building applications, whether applied on a building site or in a prefabrication (manufacturing) process. This material is also known as foamed in-situ insulation. The continuous-use temperature is within the range  $-60^{\circ}\text{C}$  to  $+80^{\circ}\text{C}$ .

The proponent has demonstrated that the product meets the following standard (see Table 1 for the performance requirements):

- CAN/ULC-S705.1-01 (including Amendments 1 and 2), "Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification."

Spray-applied rigid polyurethane foam, medium density, shall be installed by a licensed installer in accordance with the manufacturer's instructions and the following standard:

- CAN/ULC-S705.2-05, "Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Application."

For compliance to CAN/ULC-S705.2, users should contact the third-party organization that has been identified by the foam manufacturer as the third party operating the field quality assurance program for the foam product (see product listing).

## Standard

**Table 1. Performance Requirements for Physical Properties**

Property	Unit	Requirement	
		Minimum	Maximum
Air permeance (mandatory material testing)	L/s @ 75 Pa	No min.	0.02
Air permeance (optional system testing)	L/s @ 75 Pa	No min.	0.05
Apparent core density	kg/m <sup>3</sup>	28	No max.
Compressive strength	kPa	170	No max.
Dimensional stability volume change at:			
• -20°C	%	No min.	-1
• 80°C	%	-1	+8
• 70°C, 97 ± 3% RH	%	No min.	+14
Surface burning characteristics			
• flame spread	No units	No min.	500 <sup>(1)</sup>
Open-cell content volume	%	No min.	8
Initial thermal resistance of a 50-mm-thick specimen after 3 days at 23 ± 2°C	m <sup>2</sup> ·°C/W	2.5	No max.
Conditioned thermal resistance of a 50-mm-thick specimen after			
• 180 days at 23 ± 2°C or	m <sup>2</sup> ·°C/W	Declare	No max.
• 90 days at 60 ± 2°C			
Long-term thermal resistance of a 50-mm-thick specimen	m <sup>2</sup> ·°C/W	1.8 2.0	No max.
• Type 1			
• Type 2			
Tensile strength	kPa	200	No max.
Volatile organic emissions	No units	Pass <sup>(2)</sup>	No max.
Water absorption by volume	%	No min.	4
Water vapour permeance of a 50-mm-thick specimen	ng/(Pa·s·m <sup>2</sup> )	No min.	60

**Notes to Table 1:**

- (1) Results are valid for qualification to the standard. As noted in the standard, “for building code purposes, the flame-spread rating shall be conducted in accordance with the code-specified flame-spread test details with respect to the number of specimens to be tested, specimens tested intact and cut specimens.”
- (2) “Pass” means that after 30 days the volatile compound emissions do not exceed the maximum indoor air concentration stated in Table 2 of CAN/ULC-S705.1.

In cases of retrofit construction (e.g. occupied buildings), CAN/ULC-S705.2 requires that a ventilation rate of 0.3 air changes be provided within the working area during the application of the product and that the working area be isolated during spraying. The same ventilation rate is required after the product has been sprayed and for the time period determined in accordance with the CAN/ULC-S705.1. See the product listing for the time period required before occupancy.

## **Labeling**

In compliance with CAN/ULC-S705.1, each liquid component container shall be identified as either polyisocyanate component ("A") or resin component ("B"). Unless otherwise specified, each container shall be marked with the following information:

- manufacturer's name;
- product name;
- type of material (e.g. insulation);
- net mass of the contents of the packaged material;
- country of manufacturer;
- lot number;
- date of manufacture;
- "use before" date;
- the means to identify their installed product; and
- conformance with "CAN/ULC-S705.1".

## **National Building Code of Canada (NBC)**

### *NBC References*

The CAN/ULC-S705.1-01 standard is referenced in the NBC 2010, Table 5.10.1.1. and Clause 9.25.2.2.(1)(g).

The CAN/ULC-S705.2-05 standard is referenced in the NBC 2010, Sentence 5.3.1.3.(3), Table 5.10.1.1 and Sentence 9.25.2.5.(1).



## **Evaluation Listing CCMC 13555-L**

MASTERFORMAT: 07 21 19.02  
Issued: 2011-12-16  
Re-evaluation due: 2014-12-16

---

# **SWD Quik-Shield 112**

## **1. Evaluation**

The product conforms to CAN/ULC-S705.1-01 (including Amendments 1 and 2), Type 1.  
For retrofit constructions the time period before occupancy is one (1) day.

## **2. Description**

A spray-applied rigid polyurethane foam of medium density. The foam system consists of two components: “SWD Quik-Shield 112- A” isocyanate and “SWD Quik-Shield 112-B” resin. The two components are mixed on site by a qualified installer with fixed-ratio positive displacement equipment.

The colour of the final cured product is pearl gray.

The long-term thermal resistance (LTTR) for 50 mm is RSI 1.83.

## **3. Standard and Regulatory Information**

See the [Preface](#) and the standard for explanation.

Intertek has been identified by SWD Urethane Company as the third-party organization that operates the field quality assurance program (FQAP) for the products in accordance with CAN/ULC-S705.2-05.

Intertek can be contacted at: (905) 678-7820.

Listing Holder: SWD Urethane Company  
PO Box 1422  
222 South Date Street  
Mesa, AZ 85210  
U.S.A.  
Tel: 480-969-8413  
Fax: 480-461-6926

Plant(s): Maricopa County, AZ, U.S.A.

*This Listing is issued by the Canadian Construction Materials Centre, a program of the Institute for Research in Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.*

*Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to <http://www.nrc-cnrc.gc.ca/eng/services/irc/ccmc.html>, or contact the Canadian Construction Materials Centre, Institute for Research in Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone (613) 993-6189. Fax (613) 952-0268.*

***NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.***